

## WW-SC SERIES SEMI-CONDUCTING TAPE

DESCRIPTION				FEATURES	
unsupported construction m contraction due to load cyc		where accomodation of expansion and not WW-SC allows conformability to dielectric cable insulations.		Self-amalgamating     Good conductive properties     Easy to apply     UV resistance	
MATERIALS	BACKING	ADHESIVE	COLOR	STANDARD SIZE (WIDTH X LENGTH)	PART NUMBER
	EPR Rubber	None	Black	.75" x 15' (19mm x 4.6m)	WW-SC-75
TECHNICAL PROPERTIES	CHARACTERISTIC	TYPICAL VALUE		TEST METHOD	
	Thickness (mils)	30		ASTM D 4325	
	Breaking strength (psi)	290		ASTM D 412	
	Elongation at break(%)	750		ASTM D 412	
	Operating temp. Continuous	194°F, 90°C		ASTM D 4325	
	Operating temp. Overload	266°F, 130°C		ASTM D 4325	
	Water absorption	0.02		ASTM D 570	
	UV resistance (visual)	Pass		ASTM D 4325	
	Volume resistivity (Ω.cm) 96h @ 73.4°F and 50% RH	870		ASTM D 4496	
RECOMMENDED USES		STORAGE		SHELF LIFE	
For electrostatic shielding on high-voltage splices and terminations, filling indents in compression connectors, rebuilding strand shielding on high-voltage splices and shielding bus or overhead connections.		In original packaging, placed in a horizontal position, covered, between 5°C and 35°C.		60 months from date of manufacture.	

Data in table represents average test results and are not to be used for specification purpose. Users should test the products' suitability for their intended use themselves.

LIMITED WARRANTY: NSI Industries LLC warrants that each of its products will be free from material and manufacture defects at the date of shipment (unless specified otherwise). NSI Industries LLC makes or gives no warranty to the distributor, its customers, or the product's end user regarding the product's merchantability and/or suitability for their/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proven to be defective, NSI Industries sole obligation and buyer's exclusive remedy shall be through the distributor, at NSI Industries' discretion, to replace, repair, or refund the product proved to be defective within the time period specified above. EXCEPT AS EXPRESSLY SET FORTH HEREIN, NSI INDUSTRIES MAKES OR GIVES NO OTHER WARRANTIES, EXPRESSED OR IMPLIED. Except where prohibited by law, NSI Industries LLC will not be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products.