

WW-SR SERIES SILICONE RUBBER TAPE

DESCRIPTION FEATURES

WW-SR is a self-amalgamating, chemically cross-linked silicone rubber tape, triangular in cross-section and featuring a center line for precise half-lapping. Track and erosion resistant, WW-SR fuses into a solid mass within minutes of application. WW-SR employs no adhesive coating, offering a non-contaminating self-cleaning surface which maintains high tracking resistance

- Unique triangular cross-section
- Self-amalgamating
- 356 °F temperature rating
- UV and oil resistant

a solid mass within minutes of application. WW-SH employs no adhesive coating, offering a non- contaminating self-cleaning surface which maintains high tracking resistance.				OV and oil resistant Rated up to 69kV Center line to guide half-lapping	
MATERIALS	BACKING	ADHESIVE	COLOR	STANDARD SIZE (WIDTH X LENGTH)	PART NUMBER
	Silicone	None	Gray	1" x 30' (25.4mm x 9.1m)	WW-SR-10
TECHNICAL PROPERTIES	CHARACTERISTIC	TYPICAL VALUE		TEST METHOD	
	Thickness (mils): Peak	20		ASTM D 2148	
	Thickness (mils): Edge	7		ASTM D 2148	
	Breaking strength (psi)	580		ASTM D 412	
	Elongation at break (%)	300		ASTM D 412	
	Fusion (78.74 mil max.)	No flag		ASTM D 2148	
	Copper corrosion (visual)	None		ASTM D 69	
	Dielectric strength (V/mil)	609.6		ASTM D 2148	
	Dielectric constant	3.0		ASTM D 150	
	Dissipation factor	0.002		ASTM D 150	
	Track resistance (h)	1000		ASTM D 2132	
	Volume resistivity (Ω.cm)	1x10 ¹⁴		ASTM D 257	
RECOMMENDED USES		STORAGE		SHELF LIFE	
For jacketing high-voltage terminations or extended dielectric cables up to 69,000 volts. Also insulates high-temperature silicone insulated cables and provides a positive oil stop in the construction of transition splices.		In original packaging, placed in a horizontal position, covered, between 5°C and 35°C.		60 months from date of manufacture.	

Data in table represents average test results and are not to be used for specification purpose. Users should test the products' suitability for their intended use themselves.

LIMITED WARRANTY: NSI Industries LLC warrants that each of its products will be free from material and manufacture defects at the date of shipment (unless specified otherwise). NSI Industries LLC makes or gives no warranty to the distributor, its customers, or the product's end user regarding the product's merchantability and/or suitability for their/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proven to be defective, NSI Industries sole obligation and buyer's exclusive remedy shall be through the distributor, at NSI Industries' discretion, to replair, or refund the product proved to be defective within the time period specified above. EXCEPT AS EXPRESSLY SET FORTH HEREIN, NSI INDUSTRIES MAKES OR GIVES NO OTHER WARRANTIES, EXPRESSED OR IMPLIED. Except where prohibited by law, NSI Industries LLC will not be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products.